

INTERNATIONAL CENTRE FOR AUTOMOTIVE TECHNOLOGY

[A Division of NATRiP Implementation Society (NATIS), Govt. of India]

Non-Transferable

TEST REPORT






C T O B M 5312

Date: 05.10.2017

- 1.0 NAME AND ADDRESS OF THE: M/s. EASTMAN AUTO & POWER LIMITED
CUSTOMER Khasra No. 315/252/1-4 Nalagarh Pinjore Highway
Nalagarh District Solan (H.P.) 174101, India
- 2.0 NAME AND ADDRESS OF THE: Same as Sr. No. 1.0
MANUFACTURER
- 3.0 CUSTOMER LETTER REF: IOCS No. CCTNEAPLMHEEG53398 Dated 19-Jul-2017
- 4.0 DESCRIPTION OF DEVICE UNDER TEST (DUT):
DUT Name : Battery Module, 12 V
Battery Type : Lead Acid Battery
Battery Capacity(Ah) : 75 Ah (Ah in 5 hrs)
Id/Model No. : AD 1006ER
Quantity : 06 Nos. (ICAT/CNG-LPG/53398/01-06)
Trade Name : ADDO
Drawing No. : EAP-ER-40-0250






- 5.0 OBJECTIVE OF THE TEST:
To validate the Safety Requirements of Traction Batteries as per AIS: 048 amended up to date
- 6.0 TEST RESULTS:
Please refer the Test requirements and Results in Annexure-I of this report.
- 7.0 CONCLUSION:
The battery specified in Sr. No. 4.0 of this test report met all the test requirements when tested as per AIS: 048 amended up to date.

Prepared By	Checked By		Approved By	 Page 1 of 7 + Dwg (01) [53398]
				
UDIT KAUL Asst. Manager	MADHUSUDAN JOSHI Dy. General Manager		PAMELA TIKKU Sr. General Manager	


DISCLAIMER




1. ICAT issues Test reports/ Extension reports/ Developmental Reports for vehicles/ parts/ components/ assemblies etc. based on the documents produced and/or prototype / vehicle(s) or sample(s) submitted by the applicant and testing thereof.
2. ICAT issues Test reports/ Extension reports/ Developmental Reports in compliance to Motor Vehicle Act/ Central Motor Vehicle Rules and their provisions as amended from time to time or any other statutory orders under which ICAT is authorized. Other Rules/Acts are outside the purview/scope of the Test reports/Extension reports/ Developmental test reports
3. Test(s) on prototype/ vehicle(s)/ sample(s) is/are carried out on the basis of standard procedures as notified under specific rules/ requested by the applicant. Results of such tests are property of bearer of Test Reports/ Extension Reports / Developmental test reports. These results cannot be disclosed unless specifically so ordered by Government, Court, etc
4. Unless otherwise supported by a separate Certificate, this Test report Extension Reports / Developmental test reports shall not be considered in isolation as valid Type approval for any vehicle
5. ICAT is not responsible for testing each vehicles/ parts/assemblies etc. for which Test Reports/ Extension reports/ Developmental test reports is issued. Further, ICAT is not responsible for ensuring manufacturing quality of the vehicles/ components/ parts/ assemblies etc. for which the Test Reports/ Extension reports/ Developmental test reports is /are issued.
6. ICAT is no way responsible for any misuse or copying any design/type/system in connection with entire vehicle/ components/parts and assemblies covered under the Test Reports/ Extension reports/ Developmental test reports is /are issued
7. Breach of any statutory provisions, of Indian laws or laws of other countries, will be sole responsibility of the customer. ICAT shall not be liable for any claims or damages made by the customer, whatsoever. The customer shall alone be liable for the same and undertakes to indemnify ICAT in this regard
8. Further, ICAT has the right, but not under obligation to initiate cancellation / withdrawal of the Test report/Extension/ Developmental test report is/are issued, in case of any fraud, misrepresentation, when it surfaces and comes in the knowledge of ICAT
9. No extract, abridgment or abstraction from this test report may be published or used to advertise the product without the written consent of the Director, ICAT, who reserves the absolute right to agree or reject all or any of the details of any items of publicity for which consent may be sought
10. The appropriate local court at Gurgaon shall have the jurisdiction in respect of any dispute, claim or liability arising out of this report.


Prepared By		Checked By	Page 2 of 7 + Dwg(01) [53398]
			
UDIT KAUL Asst. Manager		MADHUSUDAN JOSHI Dy. General Manager	

Annexure – I

1.0 TEST REQUIREMENTS AND RESULTS:




Cl. No.	Test	Test Requirements	Observations/Results
2.1 Electrical Tests			
2.1.1	Short Circuit test (Test ID:ICAT/CNG-LPG/53398/01)	 <p>Battery Condition: Fully charged (100% SOC), contained at ambient temperature. Apply a hard short in less than one second to the battery module with a conductor specified in the standard. Test Duration: 10 minutes, or until another condition occurs which prevents completion of test (i.e. component melting, etc.) Lab temperature: Not exceeding 30°C</p> <p>Acceptance Criteria: After 2 hours of observation: At the end of the test, there shall be no: a) Physical damage to the casing or mechanical parts. b) Melting of components. c) Fire or explosion. It is acceptable for the battery to become dry at the end of the test.</p>	<p>Ambient temperature : 29°C</p> <p>Conductor of $\leq 5\text{m}\Omega$ was used and short was applied for 10 minutes.</p> <p>No physical damage, explosion or melting observed.</p> <p>Satisfactory.</p>

Prepared By		Checked By	Page 3 of 7 + Dwg(01) [53398]
			
UDIT KAUL Asst. Manager		MADHUSUDAN JOSHI Dy. General Manager	


2.1.2	Over Charge test (Test ID:ICAT/ CNG-LPG/53398/02)	 <p> Battery Condition: Fully charged (100% SOC), contained at ambient temperature at $27 \pm 5^\circ\text{C}$. Duration: 10 hours The battery is to be overcharged at a constant charging current of 0.1 (C_{10}). </p> <p> Acceptance Criteria: At the end of the test, there shall be no: a) Physical damage to the casing or other mechanical parts. b) Melting of components. c) Fire or explosion. </p>	<p> Battery was charged with 8.33 A for 10 hours. </p> <p> No physical damage, melting or explosion observed. </p> <p> Satisfactory. </p>
-------	---	--	--








Innovation • Service • Excellence




Prepared By		Checked By	
			
UDIT KAUL Asst. Manager		MADHUSUDAN JOSHI Dy. General Manager	Page 4 of 7 + Dwg(01) [53398]



2.2 Mechanical Tests




2.2.1	Vibration test (Test ID: ICAT/ CNG-LPG/53398/03)	 <p> Battery Condition: Fully charged (100% SOC), contained at ambient temperature, firmly held on the vibration table in vehicle mounting position. Axis: Vertical and Horizontal axis, with battery positioned in longitudinal direction. Acceleration: 3 g (sinusoidal vibration) Frequency: 30-150 Hz Sweep rate: 1 octave per minute Duration: 2 hours in each axis Immediately after the test, discharge the battery at room temperature not exceeding 30°C, at the rate of $I = 0.2 \times \text{Battery capacity}(C_5)$ </p> <p> Acceptance Criteria: During test, there shall be no electrolyte loss. The deterioration of battery rated capacity during discharging shall not be more than 10%. At the end of the test, there shall be no: </p> <ol style="list-style-type: none"> Physical damage to the casing or other mechanical parts Fire or explosion 	<p>No electrolyte loss observed during test.</p> <p>Immediately after the test, battery was discharged at 15 A And deterioration observed was not more than 10%.</p> <p>No physical damage or explosion observed.</p> <p>Satisfactory.</p>
-------	--	---	---

Prepared By		Checked By	
			
UDIT KAUL Asst. Manager		MADHUSUDAN JOSHI Dy. General Manager	Page 5 of 7 + Dwg(01) [53398]

2.2.2	<p>Shock test (Test ID: ICAT/CNG-LPG/53398/04)</p>	  <p>Battery Condition: Fully charged (100% SOC), contained at ambient temperature not exceeding 30°C, firmly held on the vibration table in vehicle mounting position. Axis: Vertical and Horizontal axis, with battery positioned in longitudinal direction. Acceleration: 30 g (half-sine wave) No. of shocks: 10 in each axis Duration: 15 ms of each shock Immediately after the test, discharge the battery at room temperature, at the rate of $I = 0.2 \times \text{Battery capacity}(C_5)$ Acceptance Criteria: The deterioration of battery rated capacity during discharging shall not be more than 10%. At the end of the test, there shall be no: a) Physical damage to the casing or other mechanical parts b) Fire or explosion.</p>	<p>Immediately after the test, battery was discharged at 15A and deterioration observed was not more than 10%.</p> <p>No physical damage or explosion observed.</p> <p>Satisfactory.</p>
-------	---	--	---

<p><i>Prepared By</i></p>  <p>UDIT KAUL Asst. Manager</p>		<p><i>Checked By</i></p>  <p>MADHUSUDAN JOSHI Dy. General Manager</p>	<p>Page 6 of 7 + Dwg(01) [53398]</p>
---	---	--	--


2.2.3	Roll-Over Test (Battery Module) (Test ID: ICAT/CNG-LPG/53398/05)	 <p>Rotate the battery module one complete revolution in one direction, for one minute in a continuous, slow-roll fashion, and observe leakage, if any. Then rotate the battery module in 90° increments in same direction for one full revolution. Hold the battery module for one hour at each position. Acceptance Criteria: The volume of electrolyte spilled in each position shall not be more than 25 ml per module.</p>	<p>Spillage observed was less than 25ml in each position.</p> <p>Satisfactory.</p>
2.2.4	Penetration Test (Test ID: ICAT/CNG-LPG/53398/06)	 <p>The battery module shall be penetrated with a mild steel (conductive) pointed rod, which will be electrically insulated from the test fixture. Rate of penetration: 8 cm/s. Diameter of Rod: 20mm Orientation of penetration: perpendicular to the electrode plates. Minimum Depth of penetration: Through three cells or 100 mm The battery should be observed, with the rod remaining in place, for a minimum of one hour after the test. Acceptance Criteria: At the end of the test, there shall be no: a) Melting of components. b) Fire or explosion.</p>	<p>After penetration, up to a depth through three cells with a pointed mild steel rod of diameter 20mm, electrically insulated from the test fixture, no explosion, no fire and no melting observed.</p> <p>Satisfactory.</p>

<i>Prepared By</i>		<i>Checked By</i>	<p>Page 7 of 7 + Dwg(01) [53398]</p>
			
UDIT KAUL Asst. Manager		MADHUSUDAN JOSHI Dy. General Manager	


Test report no:- CT08MS312 Dated:-05.10.2017

This drawing is the sole property of M/S Eastman Auto & Power Ltd. and issued on the condition that no further disclosure is made without written permission from M/S Eastman Auto & Power Ltd.

Over all Length = $410 \pm 2\text{mm}$



310



Over all width = $172 \pm 2\text{mm}$




209 \pm 1.0mm

Note :-
Battery Should be Free from dent, scratches, dust etc

REV. DATE		DESCRIPTION				INITIALS	
Material :-	2016	NAME	SIGN	DATE	Eastman Auto & Power Ltd.		
	DRN	Mukesh		01/08/2017	Nalagah - HP - India		
Finish :-	CHD	R.K		01/08/2017			
	APPD	MDS		01/08/2017			
Scale :-	NOT TO SCALE						
Finish :-	Smooth						
Dwg. Unit :-	MM						
Unless Otherwise Specified							
Tolerance ± 0.2							
Eastman							
...Let's grow together							

GENERAL TOLERANCE (mm)		UNLESS OTHERWISE SPECIFIED	
BEYOND	(>)	TOLERANCE	(\pm)
0	1	0.05	
1	5	0.10	
5	30	0.15	
30	60	0.20	
60	300	0.30	
300	600	0.50	



Dwg. No. :- EAP-ER-40-0250

Rev. 01